



WOOD FINISHES DIRECT

The following Technical Datasheet is provided by **Bona**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Bona Natural Primer](#)

Bona Natural

Technical data sheet

Finishing



Primer designed to preserve the impression of raw, untreated wood. Highly forgiving formulation designed for easy roller application. Quick to dry and good abrasion qualities. For the lightest, most natural appearance overcoat with Bona Traffic Natural.

- Maintains the look of pure wood
- Easy roller application
- Good abrasion qualities

Technical data

Type of lacquer:	Tinted 1-component waterborne polyurethane/acrylate primer
Solids content:	≈30%
VOC:	max 60 g/lit
Dilution:	Do not dilute
Drying time:	2-3 hours (20°C/60% R.H)
Application tools:	Bona Roller (microfiber/fleece)
Application rate:	10-12 m ² /lit (≈100g-83g/m ²) per coat
Safety:	Unclassified
Cleaning:	Wipe tools free from residual material before cleaning with a minimum of water. Dried material can be removed with acetone.
Shelf life:	1 year from date of production in unopened original container
Storage/transport:	The temperature must not fall below +5°C or exceed +25°C during storage or transport
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations.
Pack size:	10 x 1 litre (50 boxes per pallet) 3 x 5 litres (44 boxes per pallet)

Preparations

Ensure floor is acclimatized to its end-use environment. The surface which is to be treated must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. It is recommended to finalize the sanding with a Bona Quattro or Multi Disc.

Allow product to reach room temperature. Optimal application conditions are between 18-25°C and 30-60% relative air humidity. High temperatures and low humidity shorten, low temperatures and high humidity lengthen drying time. **Minimum temperature for use is 13°C.**

Treatment Schedule

2x Bona Prime Natural + 1x Bona Lacquer

Note: It is not recommended to apply more than two full coats per day due to risk of excessive wood swelling.

Bona[®]

Bona Natural

Technical data sheet

Finishing



Application

1. Shake container thoroughly before use and insert the supplied filter. Pour finish into the supplied container (box + bag). It is recommended to pour through an external strainer so as to minimize the potential for lumps.
2. Apply Prime Natural using a Bona Roller (microfiber/fleece) at approx. 10-12 m²/lit (100-83 g/m²), avoiding accumulation of product.
3. When dry (approx. 2-3 hours), abrade to reduce grain raise using the Bona Scrad system or a sanding screen grit 150 or finer.*
4. Remove all dust
5. Apply an additional layer of Prime Natural before sealing the surface with one of Bona's protective lacquers.

Maintenance

Bona Prime Natural should never be used as the final treatment for timber floors.

The information provided is prepared to the best of our current knowledge but makes no claim to be complete. User is responsible for establishing that the product and recommendations herein are fit for the designated purpose, wood type and present situation before use. Bona can only guarantee the delivered product. A professional and thereby successful application of the product is beyond our control. If in doubt make a preliminary test. User is required to read and understand all information contained on package labels and safety data sheets before using this product.