



WOOD FINISHES DIRECT

The following Product Datasheet is provided by **Dulux Trade**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:
[Dulux Trade Satinwood Paint](#)

SATINWOOD

Dulux Trade Satinwood is a solvent-based satin finish formulation that is tough, hardwearing and dirt resistant. Does not require an undercoat except where a strong colour change is required.

KEY BENEFITS

- Tough, Durable Finish
- Self Undercoating
- Dirt Resistant

PRODUCT INFORMATION

Typical Use

Suitable for use on interior wood and metal surfaces.

Pack Size

1L, 2.5L and 5L.

Colour Range

See appropriate **Dulux Trade** colour literature or visit duluxtrade.co.uk.

Film Properties

Chemical Resistance: Resistant to mild chemical fume attack but where there is heavy attack, such as actual contact with chemicals, specialist paint systems may be required (contact the **AkzoNobel** Technical Advice Centre).

Heat Resistance: Generally resistant to heat up to 90°C, but some discolouration of light colours may occur at elevated temperatures.

Water Resistance: Resistant to the levels of atmospheric humidity present in normal interior environments. Not suitable for use on immersed surfaces or where there is very heavy and prolonged condensation.

Film Thickness

Film thickness will be dependent on the coverage achieved.

Wet: 50 microns.

Dry: 25 microns.

Composition (nominal)

Pigment: Lightfast Pigments.

Binder: Alkyd.

Solvent: White Spirit.

Volume Solids

PBW: 60% (nominal). Other colours will vary.

SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry) and free from all defective or poorly adhering material such as dirt, grease and wax.

New or bare surfaces should be primed with an appropriate **Dulux Trade** primer.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Any surface defects should be filled with an appropriate **Polycell** Trade **Polyfilla**.

SATINWOOD

SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE. The normal finishing process is 2 full coats of **Dulux Trade** Satinwood. However, where a strong colour change is required, then a coat of an appropriate coloured **Dulux Trade** Undercoat may be necessary.

For best colour consistency, purchase sufficient tinted paint for entire job including touch-in at one time from the same source.

NOTE: Whilst leading-edge technology has been used in the development of this product, the nature of white solvent-based paints means that they will all discolour over time. The rate of discolouration is faster on areas with no or low natural or UV light. For long-lasting whiteness, we recommend the use of a water-based formulation such as **Dulux Trade** Quick Dry Satinwood.

APPLICATION METHOD

Brush or roller only. For Health & Safety reasons relating to all solvent-based paints, spray application is not recommended.

As with all solvent-based paints, do not apply at temperatures below 5°C (as recommended by British Standard BS 6150).

Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 17m² per litre.

FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on [0333 222 70 70](tel:03332227070).

Spray Recommendations

This product should not be sprayed.

Drying Times

Single coat at standard thickness:

Touch Dry: 4-6 hours.

Recoat: 16-24 hours.

Cleaning Up

After use, remove as much product as possible from equipment before cleaning with brush cleaner.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**. Find out more at duluxtrade.co.uk/pp.

Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

VOC

EU limit value for this product (cat.: A/d): 300g/l (2010). This product contains max. 300g/l VOC. VOC content: High (25-50%).



Issued 02/14

406

SATINWOOD

Always read full Health, Safety & Environmental Information on can before use.

Safety datasheet (SDS 406) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting duluxtrade.co.uk.

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2014.



At Dulux Trade, we believe by working with our customers we can reduce waste and do more with the resources we have. Together we can create a better future for our planet. Join us at duluxtrade.co.uk/pp

AkzoNobel