



# WOOD FINISHES DIRECT

The following Technical Datasheet is provided by **Woca**

Wood Finishes Direct cannot be held liable for the information contained within this document.

For purchasing information visit:  
[Woca Pre-Colour Stain](#)

Pre-Colour is a water-based stain for unfinished and sanded interior wood surfaces, such as floors, stairs, furniture and panels. The stain colours the wood and enhances the natural wood grain.

- **Emphasizes the natural grain for a more attractive look**
- **Gives the wood a beautiful, coloured surface**
- **Can be used with all WOCA oils**

## Application area

---

For staining untreated, new, or newly sanded wooden surfaces. Ideal for all types of wood.

## Work description

---

Preparation	Product, room and floor temperature must be between 15-25°C. Wood humidity must not exceed 12%. Ensure good ventilation during application and when drying. The wood must be newly sanded, use grit 100-120 for the final sanding. Vacuum thoroughly. Clean the wood with WOCA Intensive Wood Cleaner and leave it to dry for at least 8 hours before applying the stain. Always remember to test on a less visible spot to check the compatibility of the surface with the product.
Final sanding	Grit 100-120
Treatment	Thoroughly shake the container of Pre-Colour, both before and during use. Containers with different batch numbers should be mixed to avoid colour mismatch. Apply an even coat of undiluted stain along the wood grain with WOCA Applicator. A more uniform colour is obtained if the wet stain is polished into the wood using a polishing machine and a beige pad. Use at least 1 L of Pre-Colour per 10 m <sup>2</sup> . On vertically moun ted wood, apply from top to bottom. Leave the surface to dry for 8-12 hours. Sand with a green pad to obtain a smooth surface and vacuum thoroughly.
Note	The surface must be finished using one of WOCA's oils, following the product instructions. Pre-Colour cannot be used alone as it only provides colour to the wood, and not protection.

## Drying time

---

Drying time	8-12 hours at 20°C
-------------	--------------------



Pre-Colour

**Water-based stain for interior wood**

Technical Data Sheet

26.03.2020 – p. 2/2

## Technical data

---

Binder	Water, pigments.
Density	1.01-1.03 g/ml
Shelf life	3 years from manufacturing date if unopened
Application Temperature	15-25°C
Coverage	8-10 m <sup>2</sup> /L, depending on wood type and surface
Colours	White, Grey, Black and Brown
Cleaning of tools	Water
Storage	+10-25°C. Keep out of reach of children. Do not expose to heat (e.g. sunlight). Store frost-free during winter and cool during summer (max. +25°C).
VOC	This product contains a maximum of 100 g VOC/L. The limit value is 100 g VOC/L (cat. A/k).
Packaging	2.5 L

## Maintenance and related products

---

Basic oiling	Master Colour Oil, #522072AA Diamond Oil Active, #565010A
Related products	Intensive Wood Cleaner, #551525A
Accessories	Applicator 9", #880151 Telescopic rod, #599651

## Contact

---

WOCA Denmark A/S  
Tvæervej 6  
DK - 6640 Lunderskov  
T +45 9958 5600  
info@wocadenmark.com  
wocadenmark.com

*This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pre-treatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.*